

Non-Halogen Flame Retardant For Polycarbonate and For Combination FR Systems For PC and PC/ABS

FORMULATION

The formulations shown in this guide are representative of what can be accomplished with Arichem KSS-FR Flame Retardant. Please note that to provide thinner section UL 94 V0 results various adjuncts are required. Some of the formulations may be covered by patents and it is up to the user to confirm there is no patent infringement. It must also be pointed out that various base polycarbonate resins react differently to the flame retardant and as such all formulations must be confirmed by the user.

Transparent Polycarbonate Formulations

UL 94 V0 3.2 mm using 3 MFI Polycarbonate

Formulation Component	Loading %
Polycarbonate (3 MFI)	99.80
Arichem KSS-FR	0.20

UL 94 V0 2.6 mm using 10 MFI Polycarbonate

Formulation Component	Loading %
Polycarbonate (10 MFI)	99.55
Arichem KSS-FR	0.20
Phenyl Methyl Siloxane*	0.25

UL 94 V0 1.6 mm using 20 MFI Polycarbonate

Formulation Component	Loading %
Polycarbonate (20 MFI)	95.80
Arichem KSS-FR	0.20
Phenyl Methyl Siloxane*	4.00

* Various phenyl methyl siloxanes are referenced in patents and literature. Various trade name products are General Electric Bayer PD 5, General Electric Silicones SR476, Dow Corning 556 and others. The user is cautioned to review the patent limitations on their use in polycarbonates.



KSS-FR

Translucent Polycarbonate UL 94 V0 1.6 mm Formulation using 20 MFI PC

Formulation Component	Loading %
Polycarbonate (20 MFI)	97.30
Arichem KSS-FR	0.40
Phenyl Methyl Siloxane*	2.00
PTFE	0.30

Opaque Polycarbonate UL 94 V0 1.6 mm Formulation using 10% GF 20 MFI PC

Formulation Component	Loading %
Polycarbonate (20 MFI)	87.30
Fibrous glass	10.00
Arichem KSS-FR	0.40
Phenyl Methyl Siloxane*	2.00
PTFE	0.30

KSS-FR is the potassium salt of a complex of diphenyl sulfone sulfonate and diphenyl sulfone disulfonate. This product has been used to flame retard polycarbonate for over 25 years and original patents covering its use in polycarbonate have expired.

KSS-FR does not affect the transparency of polycarbonate formulations as it has the same refractive index as polycarbonate.

KSS-FR is more economical to use than potassium perfluorobutylsulfonate.

KSS-FR is a white powder and provides flame retardant performance at fractional loading levels or at less than 0.5% by weight in the polycarbonate formulation. Therefore, it may be helpful to produce and utilize **KSS-FR** in concentrate form for more effective dispersion into the polycarbonate matrix. Several compounders are producing a 10% concentrate. Please contact us for more information.

More information, samples, and specifications for **Arichem KSS-FR** are available upon request.

For Sampling or Technical Inquiries:

Flame Retardants Associates Inc. Phone: 360-826-4308 Email: jdinnes_fra@msn.com

Or Customer Service:

Email: chemsales@arichem.com • Website: www.arichem.com

Phone: (334) 762-2314 • Fax: (334) 762-2316 • Sales Fax: (334) 762-2104

187 Sloss Industries Rd. • PO Box 747 • Ariton, AL 36311

The data and test results referred to herein are based on tests defined by flammability safety regulations and performed under laboratory conditions. They should not be construed as a representation or warranty of performance under actual fire conditions. Arichem LLC believes the information contained herein to be accurate. Any recommendations or suggestions made are without warranty or guarantee of results since conditions of use are beyond the control of Arichem LLC. Before using, the customer should determine suitability of the product for the customer's intended application. ANY REPRESENTATION OF WARRANTY, EITHER EXPRESSED OR IMPLIED, IS SPECIFICALLY DISCLAIMED INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Arichem LLC's only obligation is to replace the product or to refund purchase price at its option. In no event shall Arichem LLC be liable in tort, contract or otherwise for incidental, consequential or punitive damages. Statements contained herein shall not be construed to be a recommendation to infringe any patent. 01/08/07